



Goodrich Global  
SINCE 1983

## GEFF EZLAY

Item	Standard Reference	Main Parameter
Name		Loose Lay 5.0/0.3mm
Size	EN ISO 24342	Deviation $\leq 0.15\%$ of nominal length up to 0.5mm maximum
Overall thickness	EN ISO 24346	5.0mm
Wear layer thickness	EN ISO 24340	0.3mm
Total mass per unit area	EN ISO 23997	+13%/-10%
Squareness and straightness	EN ISO 24342	Pass
Dimensional stability after exposure to	EN ISO 23999	$\leq 0.25\%$
Curling after exposure to heat	EN ISO 23999	$\leq 2\text{mm}$
Usage Classification	EN ISO 10874	23,31
Abrasion resistance	EN 660-2	Group T
Slip Resistance	EN 13893	DS
	DIN 51130	$\geq R9$
Color fastness to artificial light	EN ISO 105 B02	$\geq 6$
Flexibility	EN ISO 24344	20mm
Effect of castor chair	ISO 4918	Pass
Impact Sound Reduction	ASTM E 492-09	IIC=58
Chemical resistance	EN ISO 26987	GOOD
Toxicity	EN 71	Non-toxic
Resistance to staining	EN ISO 26987	GOOD
Heavy metals	Rohs	ND
Phthalate	EN 14372	ND
Formaldehyde Emission	EN 717-1	E1
Fire Classification	EN 13501-1	Bfl-s1
Underfloor heating		Not more than 28°C
SVHC	REACH	Pass
	DIBT/AgBB	Pass
VOC	French VOC Regulation	A+
	California Specification 01350	Pass

